

E645 EPDM





EPDM 70 SHEETING Drinking Water - WRAS certification

FEATURES

Black EPDM sheeting for drinking water. Approved by WRAS as suitable for contact with water for domestic purposes up to 23°C.

REGULATIONS

WRAS approval num 1904541: This product has satisfied the criteria set out in BS 6920: Part 1: 2000 "Specification" and thus complies with the requirements of the Water Regulations Advisory Scheme Tests of Effect on Water Quality (BS 6920: 2000).

APPLICATIONS

Gaskets or washers cutting and manufacturing of pieces for general industrial purpose applications in contact with drinking water.

ADVANTAGES

- Very good resistance to ozone and ageing
- Excellent temperature resistance (-40/+120 °C)
- Good ratio quality/price
- Matte finish to guarantee a good surface finished quality to secure an easy unrolling.

BENEFITS

- Performance
- Legality
- Hygiene, cleanliness
- Food safety

MAINTENANCE RECOMMENDATION

Always follow manufacturer warnings and instructions when using any cleaning product.

MECHANICAL, PHYSICAL AND CHEMICAL PROPERTIES

	Measured characteristics	Standard	Value			
MECHANICAL						
	Rubber compound - black		EPDM	ı		
	Density		1.15 ±0.05	g/cm³		
	Hardness	ASTM D2240	70 ±5	Shore A		
	Tensile strength	ISO 37	≥12	MPa		
	Elongation at break	ISO 37	≥400	%		
	Tear resistance	ISO 34-1	≥35	N/mm		
Comp	ISO 815-1	≤25	%			
TEMPERATURE						
		-40/+120	°C			
AGEING						
Δ Hardness after 70h at 70 $^\circ$		ASTM D573	≤5	Shore A		
Δ Tensile strength after 70h at 70°C		ASTM D573	≤-10	%		
Δ Elongation at break after 70h at 70°C		ASTM D573	≤-30	%		
Ozone resistance, 200pphm, 48h, 38°C, 20%		ASTM D1149 Typ A	No crack			
Swelling in water, 70 h a 23°		ISO 1817	0			
CHEMICAL RESISTANCE						
Diluted acids and bases	Concentrated acids and bases	Ozone	Oils and hydrocarbons			
Very good	Good	Very good	Non su	itable		
IDENTIFICATION						
Branding						
Packaging						
Wrapping	Black polyethylene film.					
Labelling	Self-adhesive label indicating product name, dimensions, area in m2, nominal weight, and product code to allow product traceability.					
Unless typographical error, information and figures of aux technical datached are based on our experience						

Unless typographical error, information and figures of our technical datasheet are based on our experience and laboratory tests according to international standards. This data is intended to be used as a guideline only. Material performance depends on the conditions of use and the final application.

EPDM	EPDM 70 SHEETING	E645		
THICKNESS	WIDTH	LENGTH m	WEIGHT kg/m²	SIDES FINISH
1.5 ±0.25	1400 ± 2 %	15 ± 2 %	1.72	1 SMOOTH SIDE/1 SHINY SIDE
2±0.3	1400 ± 2 %	15 ± 2 %	2.29	1 SMOOTH SIDE/1 SHINY SIDE
3±0.3	1400 ± 2 %	10 ± 2 %	3.44	1 SMOOTH SIDE/1 SHINY SIDE
4±0.4	1400 ± 2 %	10 ± 2 %	4.59	1 SMOOTH SIDE/1 SHINY SIDE
5±0.4	1400 ± 2 %	10 ± 2 %	5.73	1 SMOOTH SIDE/1 SHINY SIDE

